

MOULDED RAPESEED WAX

Description: Solidified rapeseed oil

Characteristics:

	Norm	Securities	Specifications
Solidification point	ASTM D 938	30 - 50	°C
Melting point	ASTM D 3954	55 - 65	°C
Penetration at 25°C	ASTM D 1321	about 20	0.1mm
Colour	VISUAL		LIGHT IVORY

Conditioning:

Microbeads in bags of about 20kg.

30 mai 2023

Active

Distribution C OMPANY

Phone : + 33 (0) 4 75 54 35 05

Email: contact@adc-solution.com

SIREN: 432 961 134 SIRET: 432 961 134 00025

123 Rue Marie Curie – CHATEAUNEUF-DU-RHONE

SAS Active Distribution Company with a capital of 163,200 Euros – RCS 432 961 134 VALENCE – V.V.A. FR 64 432 961 134